

DEEP

- High performing blackout fabric with a light sheen and black reverse
- Standard 100 by Oeko-Tex® certified, free from harmful substances
- Washable up to 60°
- Proven acoustic properties

APPLICATIONS



Not suitable:
SG 4905

FABRIC PROPERTIES

●	Blackout
⌘	Polyester
Ⓜ	325 g/m ²
⊥	0.45 mm
← max. →	290 cm
👉	295 cm
👈	295 cm

WASHING INSTRUCTIONS

🌊	🧺 30 -1%	🧺 60 -1%	🧺 P -0.5%	🧺 P -0.5%	🧺 P -0.5%
🧺	🧺 30 -1%	🧺 P -0.5%	🧺 P -0.5%	🧺 P -0.5%	🧺 P -0.5%
🧺	🧺 P -0.5%	🧺 P -0.5%	🧺 P -0.5%	🧺 P -0.5%	🧺 P -0.5%

FEATURES / TECHNICAL PROPERTIES

☀	5
👂	Alpha-w = 0.30 / 0.55
🔥	Flame retardant
💧	Applicable in humid areas
🌊	Suitable for Wave
🧺	Only with lined fabric
🌿	Oeko-Tex
🎨	Special colours from 240 m

FIRE PROTECTION

Class 1 (EN 13773)
Type B (BS 5867-2)
CAN/ULC-S109-14



Deep

OPTICAL AND SOLAR COEFFICIENTS ($\pm 5\%$, DIN EN 410)

Colour	T_s	R_s	A_s	F_c	g_{tot}
01	0.0	4.1	95.9	0.89	0.64
02	0.0	4.1	95.9	0.89	0.64
03	0.0	4.1	95.9	0.89	0.64
05	0.0	4.1	95.9	0.89	0.64
06	0.0	4.1	95.9	0.89	0.64
07	0.0	3.2	96.8	0.90	0.65
08	0.0	3.2	96.8	0.90	0.65
10	0.0	3.9	96.1	0.89	0.64

T_s Solar transmission

A_s Solar absorption

g_{tot} Total g-value

R_s Solar reflectance


F_c Shading factor

$F_c + g_{tot}$: Value calculated with glass: $0.72 / U_g = 1.6 \text{ W/m}^2 \text{ K}$, DIN EN 13363-1

Deep




01



02




03




05




06



07



08



10

Colours shown are not binding